

# QUALITY REPORT

No. 7408-002032  
2014-08-21

JSR CORPORATION  
1-9-2 HIGASHI-SHINBASHI, MINATO-KU,  
TOKYO, JAPAN

JSR N220S	R. K. POLYMER
OUR ORDER : 01-1-0578928 141276	NET WEIGHT : 1,050 KG

I T E M	L O T No.	740619
VOLATILE MATTER	%	0.10
ASH	%	0.16
BOUND ACRYLONITRILE	%	41.6
RAW MOONEY VISCOSITY	ML1+4	57
OSCILLATING DISK CUREMETER		
ML (160° C)	DN·M	2.0
MH (160° C)	DN·M	16.9
TC10 (160° C)	MIN	4.3
TC50 (160° C)	MIN	7.0
TC90 (160° C)	MIN	20.4
CARBON BLACK IRB#7		

001-002

N. NOJIMA  
LABORATORY