

QUALITY REPORT

No. 7408-002033
2014-08-21

JSR CORPORATION
1-9-2 HIGASHI-SHINBASHI, MINATO-KU,
TOKYO, JAPAN

JSR N220SH	R. K. POLYMER
OUR ORDER : 01-1-0578929 141276	NET WEIGHT : 2,100 KG

I T E M	L O T N o.	740805
VOLATILE MATTER	%	0.14
ASH	%	0.17
BOUND ACRYLONITRILE	%	41.2
RAW MOONEY VISCOSITY	ML1+4	81
OSCILLATING DISK CUREMETER		
ML (160° C)	DN·M	2.8
MH (160° C)	DN·M	17.7
TC10 (160° C)	MIN	4.4
TC50 (160° C)	MIN	6.9
TC90 (160° C)	MIN	19.7
CARBON BLACK IRB#7		

001-002

N. NOJIMA
LABORATORY