

QUALITY REPORT

No. 7408-002031
2014-08-21

JSR CORPORATION
1-9-2 HIGASHI-SHINBASHI, MINATO-KU,
TOKYO, JAPAN

JSR N230SL	R. K. POLYMER
OUR ORDER : 01-1-0578927 141276	NET WEIGHT : 2,100 KG

I T E M	LOT No.	740519
VOLATILE MATTER	%	0.08
ASH	%	0.24
BOUND ACRYLONITRILE	%	35.1
RAW MOONEY VISCOSITY	ML1+4	42
OSCILLATING DISK CUREMETER		
ML (160° C)	DN·M	1.9
MH (160° C)	DN·M	15.5
TC10 (160° C)	MIN	3.5
TC50 (160° C)	MIN	4.2
TC90 (160° C)	MIN	12.2
CARBON BLACK IRB#7		

001-002

N. NOJIMA
LABORATORY