

M.L.A. INDUSTRIES

CORP. ADDRESS : 111/230, HARSH NAGAR ,KANPUR — 208 012

Email : sales@mlagroup.com

PH : 0512- 3069261, 2255592, 2526257, 2545548

website : www.mlagroup.com



Manufacturers of Precipitated Silica, HCS, Azodicarbonamide, Zinc, Calcium, Aluminum Stearate, Zinc Oxide (active) and PVC Stablizer

QUALITY ASSURANCE REPORT

CUSTOMER NAME : R.K. POLYMER
 PRODUCT : PRECIPITATED SILICA
 TOTAL QUANTITY : 1000 KG
 DOC NO. :

INVOICE NO. : 55
 GRADE : NK-70
 DATE : 08-Apr-2014

Sl. No	PROPERTY	SPECIFICATION	UNIT	BATCH WISE TEST VALUE
				5D/4
1	Moisture	5 +- 1.5	%	5.4
2	Bulk Density	0.12 - 0.16	gm/cc	0.15
3	pH Value	6.5 - 7.5	--	6.99
4	Water Absorption	230 - 260	%	250
5	Loss On Ignition	6.0 max	%	5.67
6	Residue on 300 Mesh	1.0 max	%	0.17
7	Colour	White powder	--	As per std

1) IR Moisture Balance (At the time of Packing) , 2) After 50 tappings , 3) By pH Meter , 5) At 1000 °C , 6) Wet Sieving , 7) Visual Observation ,

REMARKS (IF ANY)

APPROVED OR REJECTED




APPROVED BY

QC. OFFICER

* We do visual comparison of test sample with standard in powder form or aqueous slurry because it is the easiest and most reliable method for control colour / whiteness.

* Any difference on the above values must be brought to our notice with in 7 days of receipt of the consignment

* The above test results are typical and indicative. This information and our technical advice whether verbal, in writing or by way of trials are given in good faith but without warranty. It does not release you from obligation to check its validity and to test our products as to their suitability for the intended process and uses. The handling application, use and processing of our products in your formulation in the products manufactured by you are beyond our control and, therefore entirely your own responsibility.



GMP

Right Chemistry - Right People